

TECHNICAL DATA SHEET

PVC

I. Physical Properties	Norm	Unit i. e.	PVC-U
1. Specific gravity (ρ)	ISO 1183	g/cm ³	1,36
2. Water absorption	DIN 53495	%	0,2
3. Chemical resistance	DIN 53476	-	DIN 8061
4. Max. permissible service temperature (no stronger mech. stress involved)			
upper temperature limit	-	°C	60
lower temperature limit	-	°C	-15
II. Mechanical Properties			
1. Tensile strength at yield (σ_s)	ISO 527	MPa	55
2. Elongation at yield (ϵ_s)	ISO 527	%	3
3. Tensile strength at break (σ_R)	ISO 527	MPa	30
4. Elongation at break (ϵ_R)	ISO 527	%	33
5. Impact strength (a_n)	ISO 179	kJ/m ²	o.B.
6. Notch impact strength (a_k)	ISO 179	kJ/m ²	3
7. Ball indentation hardn. (Hk)/Rockwell	ISO 2039-1	MPa	120
8. Flexural strength (σ_B 3,5%)	ISO 178	MPa	90
9. Modulus of elasticity (Et)	ISO 527	MPa	3000
III. Thermal Properties			
1. Vicat softening temp. VST/B/50	ISO 306	°C	753
VST/A/50		°C	-
2. Heat deflection temp. HDT/B	ISO 75	°C	724
HDT/A		°C	-
3. Coef. of linear therm. expansion (α)	DIN 53752	K ⁻¹ x 10 ⁻⁴	0,8
4. Thermal conductivity at 20 °C (λ)	DIN 52612	W/(m*K)	0,14
IV. Electrical Properties			
1. Volume resistivity (ρ_D)	VDE 0303	Ω x cm	$\geq 10^{15}$
2. Surface resistivity (R_o)	VDE 0303	Ω	$\geq 10^{13}$
3. Dielectric constant at 1 MHz (ϵ_r)	DIN 53483		3
4. Diel. loss factor at 1 MHz ($\tan\delta$)	DIN 53483		0,01
5. Dielectric strength	VDE 0303	kV/mm	20-40
6. Tracking resistance	DIN 53480		KB 600
V. Additional Data			
1. Bondability			+
2. Physiol. indifference	EEC		+5)
	90/128		
according	FDA		+5)
3. Friction coefficient	DIN 53375		0,6
4. Flammability	UL 94		V-0
5. UV stabilisation			o
VI. Chemical Properties			
1. Acid resistance			+
2. Hydrolysis resistance (delute)			+
3. Hydrocarbonat resistance			+
4. CKW resistance			-
5. Aromatic resistance			o
6. Ketone resistance			-
7. Resistance against hot water			

Applications:

Air Purification	Filters Valves	Plating Machines
Developing Machines	Fittings Pumps	Scrubbers
Ducts	Hoods	Tanks
Electrical Boxes	Laboratory Equipment	Wastewater treatment
Etching Machines	Packaging Machines	

Options:

SHEET: Grey

Size: 2440 mm x 1220 mm & 2000 mm x 1000 mm

Thickness: 1.5 mm to 60 mm

Hexagonal & Angle available on request

ROD: Grey & Red

Length: 2000 mm

Diameters: 6 mm to 300 mm

SQUARE SECTION: Grey

Length: 2000 mm

Dimensions: 10 mm x 10 mm to
200 mm x 200 mm



Disclaimer:

All statements, technical information and recommendations contained in this publication are for informational purposes only. Cut To Size Plastics Pty. Ltd. does not guarantee the accuracy or completeness of any information contained herein and it is the customer's responsibility to conduct its own review and make its own determination regarding the suitability of specific products for any given application.